



## Nexus 316L

### 19%Cr 12%Ni 3%Mo - Stainless Steel electrode for MMA welding

Rutile Stainless Steel Electrode for the joining low Carbon Molybdenum bearing Austenitic alloys and for cladding mild steel to provide a corrosion resistant surface. Producing butt and mitre finish fillet welds that are smooth and free of spatter.

#### International Standards

<b>BS EN 1600:1997</b>	<b>AWS A5.4 - 06</b>
<b>E 19 12 3 LR 3 2</b>	<b>E316L-17</b>

#### Typical All-Weld Metal Analysis (wt%)

C	Si	Mn	S	P	Cr	Ni	Mo	Ferrite
<0.03	0.8	0.7	0.012	0.015	18.5	12.0	2.7	7

#### Typical All-weld Metal Mechanical Properties

Yield Strength N/mm <sup>2</sup>	Tensile Strength N/mm <sup>2</sup>	Elongation %	Impact Strength +20°C
>400	>560	>35	>70

#### Welding Positions

Flat butt welds, flat fillet welds and horizontal vertical fillet welds
---

#### Materials

316, 316L
-----------

#### Packaging

Size mm	2.5 x 300	3.2 x 350	4.0 x 350
Pieces/Packet	133	73	48
Pieces/Carton	532	292	192
Kg/Packet	2.5	2.5	2.5
Packs/Carton	4	4	4
Kg/Carton	10	10	10

#### Operating Requirements

DC+ AC (70ocv min)	65 – 90 A	90 – 120 A	120 – 150 A
--------------------	-----------	------------	-------------

#### Additional Information

<b>CE Certified</b>	Constructional products directive (CPD)
Certification	BS EN 10204:2004 Type 2.2
Material safety data sheet	MSDS 05
Re-dry	2 Hours @ 250°C if required
Related Nexus Products	MIG Nexus 316LSi TIG Nexus 316L